



# JC LEAD-CALCIUM

## FOR TELECOMMUNICATIONS

Capacities from 50 to 300 Ampere-hours

C&D Technologies' Power Systems Division flooded batteries are engineered to provide superior performance and reliability over the life of the product. These batteries are designed using proprietary techniques and quality components and materials for reduced maintenance and extended battery life.



### APPLICATIONS

- Telephone Central Offices
- Mobile Telephone Switching Office
- Cable Head End Sites
- Fiber Optic Regenerator Sites
- Microwave Repeater Sites
- Telephone & Internet Network Nodes

### FEATURES & BENEFITS

- Time tested epoxy post seal and reliable tongue-and-groove jar-to-cover seal designs provide increased adhesive coverage area – offering unprecedented seal integrity during service.
- Electrical testing (capacity test) on every cell prior to shipping assures performance of every battery upon delivery.
- Suspended positive plates permit free growth without pressure on jar and cover.

### SAFE OPERATION

- Standard flame-retardant covers enhance battery plant safety with self-extinguishing properties, LOI>32%, UL 94V-0.
- Snap-on, intercell connector covers provide insulation.
- Low-evaporation, flame-arrester vent to extend watering intervals and prevent external sparks from reacting with the hydrogen inside the cell.

### COST SAVINGS

- Multi-cell design offers reduced optimum space utilization (shorter racks).
- Transparent container allows visual inspection of plates.

## SPECIFICATIONS

Plates	Height	Width	Thickness
<b>Positive</b>	8.00 in (203 mm)	7.62 in (194 mm)	0.250 in (6.40 mm)
<b>Negative</b>	8.00 in (203 mm)	7.62 in (194 mm)	0.165 in (4.20 mm)
<b>Outside Negative</b>	8.00 in (203 mm)	7.62 in (194 mm)	0.120 in (3.10 mm)
<b>Electrolyte height above plates</b>	2.70 in (69 mm)		
<b>Sediment space</b>	0.81 in (20.6 mm)		
<b>Electrolyte @ 77°F (25°C)</b>	Sulfuric acid, 1.215 specific gravity nominal		
<b>Recommended Float voltages</b>	2.19 - 2.20 volts per cell		
<b>Container</b>	Thermoplastic, transparent, (SAN)		
<b>Cover</b>	High-impact, flame-retardant thermoplastic with tongue-and-groove seal. Flammability ratings: UL 94-V0; ASTM D-635 self-extinguishing		
<b>Separator</b>	Microporous with fibrous glass mat		
<b>Safety Vent Systems</b>	Flame-arrester/low-evaporation type with flip-top dust cover		
<b>Terminals</b>	Cast-lead alloy (chair type)		
<b>Special Voltages</b>	Modules with dummy cells are available.		
<b>* Optional container</b>	Transparent, flame-retardant polycarbonate. Flammability ratings: UL 94-HB; ASTM D-635 self-extinguishing		

## RATINGS TABLE: AMPERES

FV/Cell	Model	Nominal Rates @ 77°F (25°C) and 1.215 Specific Gravity (includes connector voltage drop)										
		1 min	15 min	30 min	1 hr	2 hr	3 hr	4 hr	5 hr	6 hr	8 hr	12 hr
1.75	4JC-50	67	47	36	26	17	13	11	9	8	6	5
	4JC-100	134	94	72	51	34	26	22	18	16	13	9
	4JC-150	202	141	107	77	52	40	32	27	24	19	13
	2JC-200	269	188	143	102	69	53	43	37	32	25	18
	2JC-300	403	282	215	154	103	79	65	55	48	38	27
1.78	4JC-50	59	43	33	24	16	13	10	9	8	6	4
	4JC-100	119	87	67	48	33	25	21	18	15	12	9
	4JC-150	178	130	100	72	49	38	31	26	23	18	13
	2JC-200	237	173	134	96	65	50	41	35	31	24	17
	2JC-300	356	260	201	145	98	75	62	53	46	36	26
1.81	4JC-50	51	39	31	23	16	12	10	8	7	6	4
	4JC-100	102	78	62	45	31	24	20	17	15	12	8
	4JC-150	154	117	93	68	46	36	30	25	22	18	13
	2JC-200	205	157	124	91	62	48	40	34	29	23	17
	2JC-300	307	235	186	136	93	72	59	50	44	35	25
1.85	4JC-50	40	33	27	20	14	11	9	8	7	6	4
	4JC-100	81	66	54	41	28	22	18	16	14	11	8
	4JC-150	121	99	82	61	43	33	28	24	21	17	12
	2JC-200	161	132	109	82	57	44	37	31	28	22	16
	2JC-300	242	198	163	123	85	67	55	47	41	33	24

Additional ratings and application information is available in the Battery Selection Program at [www.cdstandbypower.net](http://www.cdstandbypower.net)

Models	Cells per unit	Plates per cell	Overall Dimensions			Approx. wt. lbs (kgs)		Electrolyte per cell lbs (kgs)
			L in (mm)	W in (mm)	H in (mm)	Net filled	Dom. Packed	
4JC-50	Four cells connected in series for eight-volt units.	3	10.28 (261)	10.0 (254)	14.6 (371)	78 (35.4)	84 (38.1)	8.2 (3.7)
4JC-100		5				94 (42.6)	100 (45.4)	7.1 (3.2)
4JC-150		7				110 (50)	116 (52.6)	6.0 (2.7)
2JC-200	2x5	94 (42.6)				100 (45.4)	7.1 (3.2)	
2JC-300	2x7	110 (50)				116 (52.6)	6.0 (2.7)	

Note: Electrolyte weighs approximately 10 lbs per gallon (1.215 kgs per liter).  
For information on battery racks, please refer to brochure 12-560.

### POWER SYSTEMS DIVISION

1400 Union Meeting Road  
P.O. Box 3053 • Blue Bell, PA19422-0858  
(215) 619-2700 • Fax (215) 619-7899 • (800) 543-8630  
customersvc@cdtechno.com  
www.cdtechno.com

Any data, descriptions or specifications presented herein are subject to revision by C&D Technologies, Inc. without notice. While such information is believed to be accurate as indicated herein, C&D Technologies, Inc. makes no warranty and hereby disclaims all warranties, express or implied, with regard to the accuracy or completeness of such information. Further, because the product(s) featured herein may be used under conditions beyond its control, C&D Technologies, Inc. hereby disclaims all warranties, either express or implied, concerning the fitness or suitability of such product(s) for any particular use or in any specific application or arising from any course of dealing or usage of trade. The user is solely responsible for determining the suitability of the product(s) featured herein for user's intended purpose and in user's specific application.

Copyright 2007 C&D TECHNOLOGIES, INC. Printed in U.S.A. 12-317-T 5M/0307/HVG